



# HIFULL HB-132

## HYDROPHOBIC FUMED SILICA

HB-132 is hydrophobic fumed silica which is produced by hydrophilic fumed silica with specific surface area of 200m<sup>2</sup>/g after chemical post-treatment with HMDS (Hexamethyldisilazane).

### 01 Applications

- Silicone rubber
- Defoamer
- Toner
- Adhesives & Sealants

### 02 Properties

- Low thickening effect and excellent processability enable high loading in polymers
- Excellent reinforcing properties in silicone rubber especially at high filler loading levels (RTV-1, RTV-2, LSR)
- High transparency
- Free flow aid for powders

### 03 Physical & Chemical Data

Properties	Unit	Typical Value	Testing Standard
Specific Surface Area (BET)	m <sup>2</sup> /g	140±20	GB/T 20020
Carbon Content ( Based on material dried at 105°C for 2 hours)	%	2.0~4.0	GB/T 20020
PH (4% suspension) ( water : ethanol is 1:1 )	—	6.0~9.0	GB/T 20020
Loss on drying( 2 hours at 105°C)	%	≤0.7	GB/T 20020
Loss on ignition (2 hours at 1000°C, based on material dried for 2 hours at 105°C)	%	≤4.0	GB/T 20020
Tamped Density (Based on material dried at 105°C for 2 hours)	g/L	45~65	GB/T 20020
Silica Content (Based on ignited material)	%	≥99.8	GB/T 20020

※ customized products available for special physical or chemical data